

## Product information

**GASTON GT** Range battery is the most standard and the first generation delicate product in our company. The definition of GT is coming from General purpose. Therefore, this range product has possessed various functions. It is individually applied to any kind of power use requirement by means of different models.

## General Purpose GT Range

### General features and benefits

#### Maintenance free

- Fluid infusion unnecessary
- Equalizing charge unnecessary

#### Superior reliability and quality

- ISO9001 has been carried out through the whole process of the manufacturing to make sure the perfect product reliability and quality. No environmental pollution and corrosion to the devices
- No acid spilled or gas occurred when using

#### High power density

- High output power and low impedance
- Low self-discharge
- After full charge, battery can keep 80% of the initial capacity when rested for 3 months
- Better anti-charge and anti-discharge performance

#### Standard

- Battery dimensions comply with JIS C8702-1995 standard

### Applications

GASTON GT range batteries incorporate advanced VRLA technology designed for 3-5 year design life @ 25°C (77°F) and high performance in:

- Alarm systems
- Cable television
- Electronic cash registers electric test equipment
- Emergency lighting systems
- Fire & security systems
- Power tools
- Toys
- UPS
- Telecom systems
- Emergency power system
- Stand-by electric power control equipment



## Discharge data (Amperes,25°C)

Battery Model	End Voltage per cell	Discharge characteristics (Amperes,25°C)								
		5Min	10Min	15Min	30Min	1h	3h	5h	10h	20h
GT2-4.5 GT4-4.5	1.70	16.6	11.0	8.47	5.40	3.50	1.16	0.74	0.42	0.23
	1.75	15.6	10.6	8.15	5.12	3.34	1.13	0.72	0.42	0.23
	1.80	14.5	10.1	7.48	4.75	3.13	1.08	0.67	0.40	0.22
GT4-9.5	1.70	33.9	21.7	17.7	10.0	6.50	2.30	16.4	0.92	0.48
	1.75	32.1	21.1	17.0	9.50	6.20	2.26	1.60	0.90	0.48
	1.80	28.7	20.0	15.6	8.80	5.80	2.16	1.50	0.84	0.46
GT6-1.3	1.70	4.15	2.68	2.09	1.20	0.78	0.28	0.20	0.11	0.06
	1.75	3.91	2.64	2.03	1.14	0.74	0.27	0.19	0.11	0.06
	1.80	3.63	2.55	1.87	1.05	0.70	0.26	0.18	0.10	0.06
GT6-2.8	1.70	6.55	4.34	3.32	1.75	1.14	0.41	0.32	0.21	0.13
	1.75	6.15	4.20	3.18	1.65	1.10	0.39	0.32	0.21	0.12
	1.80	5.70	4.04	2.96	1.55	1.00	0.38	0.30	0.20	0.12
GT6-3.4	1.70	12.1	8.00	5.99	3.50	2.30	0.82	0.57	0.33	0.18
	1.75	11.4	7.74	5.80	3.30	2.20	0.79	0.56	0.32	0.18
	1.80	10.5	7.42	5.45	3.10	2.00	0.76	0.52	0.31	0.17
GT6-4.2 GT6-4.2(S)	1.70	14.1	9.15	7.11	4.50	2.92	1.05	0.74	0.39	0.20
	1.75	13.2	8.87	6.80	4.27	2.79	1.02	0.72	0.38	0.20
	1.80	11.9	8.48	6.23	3.96	2.61	0.97	0.67	0.37	0.19
GT6-4.5 GT6-4.5(S)	1.70	14.4	9.15	7.11	4.50	2.92	1.05	0.74	0.42	0.23
	1.75	13.5	8.87	6.80	4.27	2.79	1.02	0.72	0.42	0.23
	1.80	12.1	8.48	6.23	3.96	2.61	0.97	0.67	0.40	0.22
GT6-7	1.70	24.2	16.0	12.4	7.00	4.55	1.63	1.14	0.66	0.35
	1.75	23.7	15.5	12.0	6.65	4.34	1.58	1.12	0.65	0.35
	1.80	21.2	14.8	10.9	6.16	4.06	1.52	1.01	0.63	0.34
GT6-8.5	1.70	28.5	18.3	14.0	8.00	5.20	1.86	1.31	0.76	0.40
	1.75	27.1	17.8	13.6	7.60	4.96	1.81	1.28	0.74	0.40
	1.80	24.2	16.9	12.5	7.04	4.64	1.73	1.20	0.72	0.39
GT6-10	1.70	35.7	22.9	17.7	10.0	6.50	2.30	1.64	0.94	0.50
	1.75	33.8	22.2	17.0	9.50	6.20	2.26	1.60	0.93	0.50
	1.80	30.2	21.1	15.6	8.80	5.80	2.16	1.50	0.90	0.49
GT6-12	1.70	42.8	27.5	21.2	11.4	7.41	2.80	1.97	1.12	0.60
	1.75	40.6	26.6	20.5	10.8	7.06	2.72	1.92	1.12	0.60
	1.80	37.3	25.4	18.7	10.0	6.61	2.60	1.80	1.08	0.58
GT6-200	1.70	526	386	306	192	118	50.5	32.1	19.0	10.5
	1.75	475	358	293	188	116	49.0	31.3	18.2	10.2
	1.80	340	275	233	172	109	46.9	30.4	17.1	10.0

## Discharge data (Watts/Cell,25°C)

Battery Model	End Voltage per cell	Discharge characteristics (Watts/Cell,25°C)								
		5Min	10Min	15Min	30Min	45MIN	1h	2h	3h	5h
GT2-4.5 GT4-4.5	1.70	30.7	20.9	16.1	9.75	7.11	5.85	3.50	2.23	1.42
	1.75	29.7	20.7	15.9	9.35	6.86	5.75	3.41	2.20	1.40
	1.80	28.3	20.1	14.9	8.77	6.59	5.43	3.29	2.13	1.32
GT4-9.5	1.70	62.9	41.4	33.7	19.0	14.2	11.7	7.00	4.41	3.14
	1.75	61.1	41.1	33.3	18.5	13.7	11.5	6.82	4.40	3.12
	1.80	56.6	39.9	31.0	17.5	13.2	10.8	6.58	4.22	2.97
GT6-1.3	1.70	7.68	5.23	4.04	2.25	1.71	1.41	0.84	0.53	0.39
	1.75	7.44	5.20	4.00	2.18	1.65	1.38	0.82	0.51	0.37
	1.80	7.08	5.04	3.72	2.10	1.58	1.30	0.79	0.49	0.36
GT6-2.8	1.70	15.2	9.98	7.74	4.37	3.27	2.69	1.61	1.04	0.79
	1.75	14.7	9.94	7.60	4.18	3.16	2.65	1.57	1.02	0.77
	1.80	13.5	9.66	7.13	4.03	3.03	2.50	1.51	0.97	0.74
GT6-3.4	1.70	22.4	15.2	11.8	6.85	4.98	4.10	2.45	1.57	1.07
	1.75	21.7	15.1	11.6	6.50	4.81	4.03	2.39	1.54	1.04
	1.80	20.6	14.7	10.8	6.14	4.61	3.80	2.30	1.49	1.00
GT6-4.2 GT6-4.2(S)	1.70	27.0	17.4	13.4	8.55	6.40	5.27	3.15	1.95	1.37
	1.75	25.7	17.3	13.3	8.28	6.18	5.18	3.07	1.88	1.35
	1.80	23.6	16.8	12.4	7.89	5.93	4.89	2.96	1.80	1.27
GT6-4.5 GT6-4.5(S)	1.70	27.0	17.4	13.4	8.55	6.40	5.27	3.15	2.05	1.42
	1.75	25.7	17.3	13.3	8.28	6.18	5.18	3.07	1.98	1.40
	1.80	23.6	16.8	12.4	7.89	5.93	4.89	2.96	1.90	1.32
GT6-7	1.70	44.8	30.5	23.6	13.3	9.95	8.20	4.90	3.17	2.18
	1.75	45.1	30.4	23.4	12.9	9.61	8.06	4.77	3.09	2.16
	1.80	41.3	29.4	21.7	12.3	9.23	7.60	4.60	3.00	2.09
GT6-8.5	1.70	52.8	34.9	26.9	15.2	11.4	9.37	5.60	3.58	2.52
	1.75	51.6	34.8	26.7	14.5	11.0	9.21	5.46	3.52	2.47
	1.80	47.2	33.6	24.8	14.0	10.5	8.67	5.26	3.42	2.36
GT6-10	1.70	66.2	43.6	33.7	19.0	14.2	11.7	7.00	4.41	3.14
	1.75	64.3	43.3	33.3	18.5	13.7	11.5	6.82	4.40	3.12
	1.80	59.0	42.0	31.0	17.5	13.2	10.8	6.58	4.22	2.97
GT6-12	1.70	79.2	52.3	40.4	21.6	17.1	14.1	8.40	6.13	4.02
	1.75	77.2	52.0	40.0	21.1	16.5	13.8	8.18	5.95	3.91
	1.80	72.8	50.4	37.2	19.8	15.8	13.0	7.90	5.74	3.77
GT6-200	1.70	964	708	562	319	289	236	199	97.8	64.5
	1.75	845	659	528	300	276	231	186	96.4	63.6
	1.80	677	546	461	281	260	215	175	92.7	59.3

## Discharge data (Amperes, 25°C)

Battery Model	End Voltage per cell	Discharge characteristics (Amperes, 25°C)								
		5Min	10Min	15Min	30Min	1h	3h	5h	10h	20h
GT12-1.3	1.70	4.15	2.68	2.09	1.20	0.78	0.28	0.20	0.11	0.06
	1.75	3.91	2.64	2.03	1.14	0.74	0.27	0.19	0.11	0.06
	1.80	3.63	2.55	1.87	1.05	0.70	0.26	0.18	0.10	0.06
GT12-2.2	1.70	7.20	4.57	3.55	2.25	1.46	0.53	0.37	0.20	0.11
	1.75	6.75	4.43	3.40	2.13	1.40	0.51	0.36	0.20	0.10
	1.80	6.05	4.24	3.11	1.98	1.31	0.48	0.35	0.19	0.10
GT12-3.4	1.70	11.1	7.31	5.40	3.20	2.08	0.75	0.52	0.30	0.16
	1.75	10.1	7.07	5.32	3.04	1.98	0.72	0.51	0.30	0.16
	1.80	9.69	6.76	4.96	2.82	1.86	0.69	0.48	0.28	0.15
GT12-4.2	1.70	14.1	9.15	7.11	4.50	2.92	1.05	0.74	0.39	0.20
	1.75	13.2	8.87	6.80	4.27	2.79	1.02	0.72	0.38	0.20
	1.80	11.9	8.48	6.23	3.96	2.61	0.97	0.67	0.37	0.19
GT12-4.5	1.70	14.4	9.15	7.11	4.50	2.92	1.05	0.74	0.42	0.23
	1.75	13.5	8.87	6.80	4.27	2.79	1.02	0.72	0.42	0.23
	1.80	12.1	8.48	6.23	3.96	2.61	0.97	0.67	0.40	0.22
GT12-7.2	1.70	24.2	16.0	12.4	7.00	4.55	1.63	1.14	0.66	0.35
	1.75	23.7	15.5	12.0	6.65	4.34	1.58	1.12	0.65	0.35
	1.80	21.2	14.8	10.9	6.16	4.06	1.52	1.05	0.63	0.34
GT12-8.5	1.70	28.8	19.8	15.2	9.00	5.85	2.22	1.48	0.85	0.45
	1.75	27.7	18.7	14.7	8.55	5.58	2.13	1.44	0.85	0.45
	1.80	25.7	18.0	13.3	7.72	5.22	2.04	1.35	0.81	0.44
GT12-10	1.70	35.7	22.9	17.7	10.0	6.50	2.30	1.64	0.94	0.50
	1.75	33.8	22.2	17.0	9.50	6.20	2.26	1.60	0.93	0.50
	1.80	30.2	21.1	15.6	8.80	5.80	2.16	1.50	0.90	0.49
GT12-12	1.70	42.8	27.5	21.2	11.4	7.41	2.80	1.97	1.12	0.60
	1.75	40.6	26.6	20.5	10.8	7.06	2.72	1.92	1.12	0.60
	1.80	37.3	25.4	18.7	10.0	6.61	2.60	1.80	1.08	0.58
GT12-18	1.70	63.5	42.8	32.0	19.0	13.1	4.97	3.39	1.70	0.90
	1.75	60.3	41.7	31.3	18.2	12.5	4.85	3.32	1.68	0.90
	1.80	56.3	39.5	29.5	17.2	11.6	4.68	3.25	1.63	0.88
GT12-26	1.70	80.6	50.1	37.8	22.0	15.8	6.92	3.90	2.18	1.20
	1.75	75.8	48.4	36.2	20.8	15.2	6.74	3.84	2.18	1.20
	1.80	70.4	46.5	33.6	19.6	15.0	6.56	3.60	2.06	1.19

## Discharge data (Amperes, 25°C)

Battery Model	End Voltage per cell	Discharge characteristics (Amperes, 25°C)								
		5Min	10Min	15Min	30Min	1h	3h	5h	10h	24h
GT12-35	1.70	92.2	67.7	54.1	34.4	20.7	8.71	5.77	3.30	1.52
	1.75	83.5	62.9	51.4	33.4	20.4	8.50	5.67	3.15	1.47
	1.80	60.0	48.5	41.2	30.9	19.1	8.19	5.35	2.94	1.42
GT12-40	1.70	101	74.7	59.6	37.9	23.4	9.50	6.30	3.60	1.66
	1.75	91.8	69.4	56.7	36.8	22.9	9.30	6.10	3.40	1.50
	1.80	66.0	53.5	45.3	33.8	20.8	8.90	5.80	3.30	2.84
GT12-55	1.70	146	107	85.9	54.6	32.4	13.8	9.10	5.30	2.40
	1.75	132	100	81.6	53.0	32.1	13.5	8.90	5.00	2.30
	1.80	95.1	77.1	65.3	48.8	30.1	12.9	8.50	4.70	2.24
GT12-65	1.70	171	126	101	63.7	38.2	16.3	10.6	6.20	2.84
	1.75	155	117	96.0	61.7	37.4	15.8	10.4	5.90	2.70
	1.80	112	76.8	76.8	57.2	35.7	15.3	10.0	5.60	2.65
GT12-70	1.70	180	132	106	66.9	40.1	17.1	11.1	6.51	2.98
	1.75	163	123	101	64.8	39.3	16.6	10.9	6.20	2.84
	1.80	118	95.2	81.6	60.1	37.5	16.1	10.5	5.88	2.78
GT12-80	1.70	212	156	124	78.4	47.0	20.2	13.2	7.60	3.50
	1.75	192	145	118	76.0	46.1	19.6	13.0	7.40	3.30
	1.80	138	112	95.2	70.5	44.1	18.9	12.3	6.90	3.25
GT12-90	1.70	232	171	134	84.0	50.0	22.1	14.7	8.40	3.78
	1.75	212	159	140	86.6	51.0	22.7	14.9	8.70	3.98
	1.80	168	121	114	80.2	47.6	21.9	14.1	8.10	3.91
GT12-100	1.70	266	195	155	98.0	58.8	25.2	16.5	9.60	4.37
	1.75	240	181	148	95.0	57.6	24.5	16.2	9.20	4.10
	1.80	172	139	118	87.4	52.1	23.6	15.3	8.60	4.08
GT12-120	1.70	320	235	187	117	71.2	30.3	18.8	11.4	5.25
	1.75	289	218	178	114	70.3	29.4	18.2	10.9	5.00
	1.80	207	168	142	105	66.0	28.3	17.4	10.3	4.85
GT12-150	1.70	393	288	229	144	88.5	37.8	24.8	14.2	6.56
	1.75	355	267	219	141	87.8	36.7	24.2	13.6	6.20
	1.80	254	205	175	129	82.1	35.2	22.8	12.8	6.12
GT12-200	1.70	526	386	306	192	118	50.5	32.1	19.0	8.75
	1.75	475	358	293	188	116	49.0	31.3	18.2	8.20
	1.80	340	275	233	172	109	46.9	30.4	17.1	8.15

## Discharge data (Watts/Cell,25°C)

Battery Model	End Voltage per cell	Discharge characteristics (Watts/Cell,25°C)								
		5Min	10Min	15Min	30Min	45MIN	1h	2h	3h	5h
GT12-1.3	1.70	7.68	5.23	4.04	2.25	1.71	1.41	0.84	0.53	0.39
	1.75	7.44	5.20	4.00	2.18	1.65	1.38	0.82	0.51	0.37
	1.80	7.08	5.04	3.72	2.10	1.58	1.30	0.79	0.49	0.36
GT12-2.2	1.70	13.5	8.70	6.70	4.27	3.20	2.63	1.57	1.02	0.71
	1.75	12.8	8.65	6.65	4.24	3.09	2.59	1.53	0.99	0.70
	1.80	11.8	8.40	6.20	3.94	2.96	2.44	1.48	0.95	0.66
GT12-3.4	1.70	20.5	13.9	10.7	5.99	4.55	3.75	2.24	1.44	1.00
	1.75	19.2	13.8	10.6	5.82	4.39	3.68	2.18	1.40	0.98
	1.80	18.9	13.4	9.92	5.61	4.21	3.47	2.10	1.35	0.94
GT12-4.2	1.70	27.0	17.4	13.4	8.55	6.40	5.27	3.15	1.95	1.37
	1.75	25.7	17.3	13.3	8.28	6.18	5.18	3.07	1.88	1.35
	1.80	23.6	16.8	12.4	1.89	5.93	4.89	2.96	1.80	1.27
GT12-4.5	1.70	27.0	17.4	13.4	8.55	6.40	5.27	3.15	2.05	1.42
	1.75	25.7	17.3	13.3	8.28	6.18	5.18	3.07	1.98	1.40
	1.80	23.6	16.8	12.4	7.89	5.93	4.89	2.96	1.90	1.32
GT12-7.2	1.70	44.8	30.5	23.6	13.3	9.95	8.20	4.90	3.17	2.28
	1.75	45.1	30.4	23.4	12.9	9.61	8.06	4.77	3.09	2.26
	1.80	41.3	29.4	21.7	12.3	9.23	7.60	4.60	3.00	2.19
GT12-8.5	1.70	54.4	37.1	28.6	16.8	11.9	10.4	5.88	4.30	2.81
	1.75	52.7	36.8	28.3	16.1	11.5	10.3	5.72	4.16	2.74
	1.80	50.1	35.7	26.3	14.8	11.1	10.1	5.52	4.02	2.64
GT12-10	1.70	66.2	43.6	33.7	19.0	14.2	11.7	7.00	4.41	3.14
	1.75	64.3	43.3	33.3	18.5	13.7	11.5	6.82	4.40	3.12
	1.80	59.0	42.0	31.0	17.5	13.2	10.8	6.58	4.22	2.97
GT12-12	1.70	79.2	52.3	40.4	22.5	17.1	14.1	8.40	6.13	4.02
	1.75	77.2	52.0	40.0	21.8	16.5	13.8	8.18	5.95	3.91
	1.80	72.8	50.4	37.2	21.0	15.8	13.0	7.90	5.74	3.77
GT12-18	1.70	119	80.5	61.1	35.8	28.2	21.9	13.9	8.54	6.30
	1.75	111	78.6	60.6	34.9	27.3	21.6	13.6	8.43	6.24
	1.80	104	71.4	57.7	33.8	26.4	20.5	13.2	8.18	6.00
GT12-26	1.70	163	103	80.0	42.5	31.6	24.6	15.8	11.3	7.74
	1.75	156	101	79.0	42.0	31.5	24.5	15.4	10.9	7.52
	1.80	154	99.0	78.0	41.0	31.0	24.0	14.8	10.5	7.24

## Discharge data (Watts/Cell,25°C)

Battery Model	End Voltage per cell	Discharge characteristics (Watts/Cell,25°C)								
		5Min	10Min	15Min	30Min	1h	3h	5h	10h	24h
GT12-35	1.70	179	129	103	68.2	40.3	17.6	11.7	6.70	2.97
	1.75	161	120	97.0	65.6	40.1	17.3	11.5	6.49	2.95
	1.80	147	109	87.0	59.8	38.8	16.7	10.8	6.05	2.73
GT12-40	1.70	191	140	109	71.7	44.3	18.5	12.2	6.90	3.10
	1.75	171	130	102	69.0	44.0	18.2	12.1	6.80	3.00
	1.80	159	108	89.2	62.9	40.9	17.6	11.2	6.40	2.90
GT12-55	1.70	262	198	152	93.9	61.4	26.8	17.8	10.0	4.50
	1.75	235	183	147	90.8	60.5	26.4	17.4	9.90	4.50
	1.80	189	153	128	79.2	58.9	25.3	16.4	9.30	4.40
GT12-65	1.70	308	232	184	112	75.7	31.6	20.8	11.7	5.40
	1.75	276	216	172	105	75.2	31.1	20.6	11.6	5.30
	1.80	221	179	150	97.0	69.9	30.0	19.3	11.0	5.00
GT12-70	1.70	323	244	193	118	79.5	33.2	21.8	12.3	5.76
	1.75	290	227	187	110	79.0	32.6	21.6	12.2	5.56
	1.80	232	188	158	102	73.4	31.5	20.2	11.6	5.25
GT12-80	1.70	381	286	227	142	95.5	39.1	25.8	14.5	6.50
	1.75	341	267	213	140	92.8	38.5	25.5	14.3	6.50
	1.80	274	221	186	131	86.6	37.3	23.8	13.6	6.20
GT12-90	1.70	442	310	248	151	104	44.3	28.7	16.4	7.30
	1.75	387	288	237	145	102	43.6	28.3	16.2	7.30
	1.80	311	236	206	134	96.2	41.5	26.2	15.3	6.90
GT12-100	1.70	476	358	284	164	112	48.9	32.3	18.0	8.20
	1.75	427	333	267	156	110	48.2	31.8	17.9	8.20
	1.80	342	276	233	142	105	46.6	29.8	17.1	7.70
GT12-120	1.70	572	431	342	191	139	58.6	38.2	21.8	9.90
	1.75	513	401	321	179	137	57.7	38.1	21.4	9.90
	1.80	412	332	280	158	129	55.8	35.7	20.5	9.20
GT12-150	1.70	704	529	420	249	174	73.3	48.4	27.3	12.3
	1.75	632	492	395	236	173	72.3	47.7	26.8	12.3
	1.80	506	408	345	216	161	69.4	44.4	25.5	11.5
GT12-200	1.70	964	708	562	319	236	97.8	64.5	36.2	16.4
	1.75	845	659	528	300	231	96.4	63.6	35.8	16.4
	1.80	677	546	461	281	215	92.7	59.3	34.0	15.3

## General Specifications

Type	Nominal Capacity(Ah)		Dimensions in millimeters and (inches)				Approx Weight kg(Lb)
	Nominal Voltage(V)	C <sub>20</sub> to 1.80Vpc	Length	Width	High	Total Height	
GT2-4.5	2	4.5	47.0 (1.85)	26.0 (1.02)	101 (3.98)	107 (4.21)	0.31 (0.70)
GT2-10	2	10	52.5 (2.07)	50.0 (1.97)	93.3(3.67)	99.3 (3.91)	0.73 (1.61)
GT4-4.5	4	4.5	48.0 (1.89)	48.0 (1.89)	102 (4.02)	108 (4.25)	0.62 (1.37)
GT4-9.5	4	9.5	102 (4.02)	44.0 (1.73)	95.0 (3.74)	101 (3.98)	1.15 (2.53)
GT6-1.3	6	1.3	97.0 (3.82)	24.0 (0.95)	52.0 (2.05)	58.0 (2.28)	0.31 (0.70)
GT6-2.8	6	2.8	66.0 (2.60)	33.0 (1.30)	97.0 (3.82)	104 (4.09)	0.61 (1.30)
GT6-3.4	6	3.4	134 (5.28)	35.0 (1.38)	61.0 (2.40)	67.0 (2.64)	0.65 (1.40)
GT6-4.2	6	4.2	70.0 (2.76)	47.0 (1.85)	101 (3.98)	107 (4.21)	0.85 (1.90)
GT6-4.2(S)	6	4.2	70.0 (2.76)	47.0 (1.85)	101 (3.98)	107 (4.21)	0.85 (1.90)
GT6-4.5	6	4.5	70.0 (2.76)	47.0 (1.85)	101 (3.98)	107 (4.21)	0.85 (1.90)
GT6-4.5(S)	6	4.5	70.0 (2.76)	47.0 (1.85)	101 (3.98)	107 (4.21)	0.85 (1.90)
GT6-5L	6	5	67.0 (2.64)	67.7 (2.65)	96.5 (3.80)	116(4.56)	1.00 (1.98)
GT6-7	6	7	151 (5.95)	34.0 (1.34)	94.0 (3.70)	100 (3.94)	1.36 (3.00)
GT6-8.5	6	8.5	151 (5.95)	50.0 (1.97)	94.0 (3.70)	100 (3.94)	1.85 (4.10)
GT6-10	6	10	151 (5.95)	50.0 (1.97)	94.0 (3.70)	100 (3.94)	1.85 (4.10)
GT6-12	6	12	151 (5.95)	50.0 (1.97)	94.0 (3.70)	100 (3.94)	2.10 (4.60)
GT6-12T	6	12	108 (4.24)	70.8 (2.79)	140 (5.51)	140 (5.51)	2.50 (5.51)
GT6-200	6	200	320 (12.6)	175 (6.89)	226 (8.89)	231 (9.09)	31.0 (68.4)
GT8-3.3	8	3.3	67.0 (2.64)	48.0 (1.89)	90.0 (3.54)	90.0 (3.54)	0.78 (1.72)
GT12-0.8	12	0.8	96.0 (3.78)	25.0 (0.98)	61.5 (2.42)	61.5 (2.42)	0.36 (0.80)
GT12-1.3	12	1.3	97.0 (3.82)	43.0 (1.69)	52.0 (2.05)	58.0 (2.8)	0.61 (1.30)
GT12-2.2	12	2.2	103 (4.06)	46.0 (1.81)	70.0 (2.76)	70.0 (2.76)	0.98 (2.20)
GT12-3.4	12	3.4	134 (5.28)	67.0 (2.64)	61.0 (2.40)	67.0 (2.64)	1.40 (3.10)
GT12-4.2	12	4.2	90.0 (3.54)	70.0 (2.76)	101 (3.98)	107 (4.21)	1.72 (3.80)
GT12-4.5	12	4.5	90.0 (3.54)	70.0 (2.76)	101 (3.98)	107 (4.21)	1.72 (3.80)
GT12-7	12	7	151 (5.95)	65.0 (2.56)	95.0 (3.74)	101 (3.98)	2.30 (5.08)
GT12-7.2	12	7.2	151 (5.95)	65.0 (2.56)	95.0 (3.74)	101 (3.98)	2.66 (5.88)
GT12-8.5	12	8.5	151 (5.95)	65.0 (2.56)	95.0 (3.74)	101 (3.98)	2.82 (6.23)
GT12-10	12	10	151 (5.95)	98.0 (3.86)	95.0 (3.74)	101 (3.98)	4.20 (9.30)
GT12-12	12	12	151 (5.95)	98.0 (3.86)	95.0 (3.74)	101 (3.98)	4.20 (9.30)
GT12-18	12	18	181 (7.13)	77.0 (3.03)	167 (6.58)	167 (6.58)	5.70 (12.6)
GT12-26	12	26	166 (6.54)	175 (6.89)	125 (4.92)	125 (4.92)	9.20 (20.3)
GT12-35	12	35	195 (7.68)	130 (5.12)	159 (6.26)	180 (7.09)	10.0 (22.5)
GT12-40	12	40	197 (7.76)	165 (6.50)	170 (6.69)	170 (6.69)	13.5 (29.8)
GT12-55	12	55	230 (9.04)	138 (5.44)	206 (8.12)	210 (8.27)	18.0 (39.7)
GT12-65	12	65	335 (14.0)	167 (6.58)	179 (7.05)	183 (7.21)	22.0 (49.0)
GT12-70	12	70	256 (10.1)	168 (6.62)	208 (8.20)	212 (8.35)	22.0 (49.0)
GT12-80	12	80	305 (12.0)	168 (6.62)	208 (8.20)	212 (8.35)	24.0 (52.9)
GT12-90	12	90	305 (12.0)	168 (6.62)	208 (8.20)	212 (8.35)	32.0 (70.6)
GT12-100	12	100	330 (13.0)	171 (6.73)	220 (8.66)	227 (8.94)	32.0 (70.6)
GT12-120	12	120	410 (16.1)	175 (6.89)	227 (8.94)	227 (8.94)	38.0 (83.8)
GT12-150	12	150	485 (19.1)	172 (6.77)	240 (9.45)	240 (9.45)	47.0 (104)
GT12-200	12	200	522 (20.6)	238 (9.37)	218 (8.58)	236 (9.29)	65.0 (143)

### GASTON BATTERY INDUSTRIA LTD

Add: 7/F,Blk B, Edwick ind Centre, 30lei Muk Rd.,  
Kwai Chung, HongKong.  
Tel: (852)24477507 Fax: (852)26172465  
E-mail: [gaston@gaston.com.hk](mailto:gaston@gaston.com.hk)  
Website: <http://www.gaston.com.hk>

### GASTON BATTERY INDUSTRIA LTD SHENZHEN OFFICE

Add: rm1913-1914, BLK.B, jingtong Building  
Number 1058 Aiguo Rd., ShenZhen,  
Guangdong, P.R.China  
Tel: 86-755-25680676 Fax: 86-755-25411738  
E-mail: [gaston@netvigator.com](mailto:gaston@netvigator.com)